US005721042A

United States Patent [19]

Iijima et al.

[11] Patent Number: 5,721,042

[45] Date of Patent: Feb. 24, 1998

[54] **ELECTROSTATIC INFORMATION RECORDING MEDIUM**

[75] Inventors: **Masayuki Iijima**; **Osamu Shimizu**; **Yuichi Nakayasu**; **Yoshiaki Tsuruoka**; **Kayoko Sugiyama**, all of Tokyo, Japan

[73] Assignee: **Dai Nippon Printing Co., Ltd.**, Tokyo, Japan

[21] Appl. No.: **618,548**

[22] Filed: **Mar. 19, 1996**

Related U.S. Application Data

[62] Division of Ser. No. 75,581, PCT/JP92/01136 Oct. 15, 1992, Pat. No. 5,527,589.

[30] **Foreign Application Priority Data**

Oct. 16, 1991	[JP]	Japan	3-267505
Oct. 17, 1991	[JP]	Japan	3-269427
Nov. 12, 1991	[JP]	Japan	3-295529
Oct. 17, 1997	[JP]	Japan	3-26948

[51] **Int. Cl.**[6] **B32B 3/00**

[52] **U.S. Cl.** **428/195**; 428/411.1; 428/421; 428/422; 428/500; 428/913; 428/914; 427/256

[58] **Field of Search** 430/122; 428/195, 428/211, 411.1, 913, 914, 421, 422, 500; 427/256

[56] **References Cited**

U.S. PATENT DOCUMENTS

3,920,330	11/1975	Wells et al.	355/3
4,294,904	10/1981	Mammino	430/122

FOREIGN PATENT DOCUMENTS

5647042	4/1981	Japan .
56113186	9/1981	Japan .
56138742	10/1981	Japan .
0264647	3/1990	Japan .
60128450	7/1995	Japan .

Primary Examiner—William Krynski
Attorney, Agent, or Firm—Dellett and Walters

[57] **ABSTRACT**

The electrostatic information recording medium of the present invention has an electric charge retaining layer **11** stacked on at least an electrode layer **13**, as shown in FIG. **1**. The electric charge retaining layer is formed from either ① a resin selected from among fluorocarbon resins and polystyrene resins, and an insulating organic substance having no photoconductivity. The electrostatic information recording medium may be produced, as shown in FIG. **5**, by stacking an insulating resin layer **10** on an electrode layer **13**, stacking a photoconductive or electrically conductive fine particle layer **11** on the insulating resin layer **10**, and further stacking an insulating resin layer **12** on the fine particle layer **11** to a thickness of 0.1 μm to 1 μm. If the insulating resin layers **10** and **12** are formed by coating using a fluorocarbon resin solution, the electrostatic information recording medium can be produced with excellent processability.

6 Claims, 13 Drawing Sheets